

COMPOSITION

Two-component pigmented epoxy modified product for the production of synthetic self-leveling mortars also suitable for installation by roller - low thickness (HP greater coverage).

VOC lim. 100 g/l - Real VOC < 35 g/l.

FIELD OF USE

Continuous flooring easy to maintain with good resistance to transit of light-wheeled vehicles, pigmented and glossy version.

Operating temperature from -10°C to +40°C.

CERTIFICATIONS

- Compliance with LEED regulations for low emitting materials, EQ Credit 4.1—4.2—4.3 reduction of the emission of pollutants (VOC) inside buildings.

QUALITY

The product is subjected to careful and constant testing in our laboratories. The raw materials used are rigorously selected and controlled.

TECHNICAL SPECIFICATIONS

RESULTS

ANALISYS METHOD

Mixing Ratio (*)

NEUTRAL version: add 100 parts of weight of Part A (BASE) with 22 parts of weight of Part B (REAGENT);

COLORED version (standard colors): add 100 parts of weight of Part A (BASE) with 21 parts of weight of Part B (REAGENT);

COLORED version (p10): add 100 parts of weight of Part A (BASE) with 19 parts of weight of Part B (REAGENT).

If necessary, add quartz inerts in appropriate grain size.

All Pava Resins products must be mixed thoroughly before proceeding with the various application phases. Manual mixing is not permitted; incorrect mixing causes the coating to not completely cure.

Combine the different components, taking care to mix thoroughly by mixing at low speed in order to obtain a homogeneous color mixture. It is recommended to take particular care in mixing all the compound inside each individual components; with the help of a spatula/knife collect the product from the sides/bottom of the pot in order to maintain the catalysis ratios.

Mix component A (Base) with a propeller/blade mixer and then add component B (reagent) and mix for a minimum of 3 minutes until the mixture is homogeneous in density and chromaticity.

For the colored version it is recommended to use the complete packaging. In the event that it is necessary to divide the packages, take care to mix properly all the colored component to disperse the pigments evenly. With the help of a precision balance, then divide the components paying careful attention in order to maintain the catalysis ratios of the individual elements, so as not to incur poor performance.

13 IST 21

Specific Weight (**)

1,35 - 1,50 gr/cm³ at 20 ± 2°C, depending on the color.

ASTM D 1475
EN ISO 2811-1

High Solid Content (**)

100 (± 1) % according to the internal test lab procedures.

ASTM D 2369
EN ISO 3251

Viscosity at 25±2°C (**)

2000 - 4500 mPa s

ASTM D 2196
EN ISO 3219

Adhesion to Concrete (*)

> 2,0 (MPa)

ASTM D 4541
EN 1542

Surface hardness Shore (*)

> 97 A

UNI EN ISO
866

Thermal Expansion Coeff. (*)

2,5 E-5 (cm/cm°C)

/



TECHNICAL SPECIFICATIONS	RESULTS	ANALISYS METHOD
Abrasion (1 kg 1000 cycles CS10) (*)	< 89 mg	ASTM 4060 EN ISO 5470/1
Fire Reaction (*)	Bfl-s1	EN 13501 - 1
Break Elongation	< 1,0	/
Resistività elettrica	10 ¹⁴ (Ω cm)	-
Dilution (*)	Ready to use.	13 IST 21
Mixture Duration (*)	Pot-life of 45 - 55 minutes at 20 ± 2°C, mixed product.	13 IST 22 EN 9514
Drying Time (*)	Touch dry after max. 10 hours at 20 ± 2°C, hardening from 4 to 6 days according to environmental temperature. Tendency to opacification and fogging with temperatures lower than 10°C and high humidity, > 70%.	ASTM D 1640 EN ISO 866
Recoating (**)	After 24/48 hours depending on temperature and thickness obtained. For compatibility and overcoating, contact our Technical Office.	ASTM D 1640
Consumption and Yield (*)	(theoretical) 1,500 - 1,800 kg/m ² , thickness about 1 mm.	13 IST 03
Appearance of the Film (*)	Polished, yellowing and chalking for exposure to. U.V., wear and aging.	/
Number of Layers	One.	/
Tools Washing	With nitro thinner.	/
Storage Life	6 months in the original well closed packing in ventilated and dry spaces at room temperature not lower than 15°C. Do not expose the packages directly to the sun. Keep away from frost.	/

(*) Tests performed according to the methods indicated in the internal control plan. The product is not self-supporting UNI10966, but conditioned by the support.
No film tests RIF. ISO UNI EN 13892 - 2 (hightickness).
(**) Typical Values

Preparation of Surfaces

Mechanical or manual abrasion, shot peening and bush-hammering.

Any imperfections or irregularities that could compromise the final aesthetic effect must be corrected by sanding and/or regularizing of the substrate before applying the subsequent products.

In the presence of cracking processes in the support, carefully check the nature of these phenomena: if due to plastic shrinkage, and if due to stress-structural phenomena affecting the support itself. Both in the case of static and dynamic cracks consult our Technical Office in order to intervene appropriately. No responsibility can fall on the product in the event that these cracking processes affect the same as, according to UNI EN 10966, these systems are not self-supporting.

Any traces of oil, grease, paint, varnish, efflorescence, etc. must be removed beforehand, as well as any chalking or removable sections.

Before proceeding with the application of Pava Resine products, the preliminary treatment of all the critical points is mandatory (possible cracks in the support, corners, edges, vertical folds, expansion and/or structural joints, drains, grids, gutter connections, drainpipes, steps and thresholds, plant pipes, etc).

Application

Notched trowel or doctor blade, with temperatures not lower than 18°C. Autopava 2K HP can be considered self-deaerating; incorrect mixing of the 2 components (low homogenization) may promote suboptimal performance. Since the film produced is almost waterproof, bubbles or detachments can be generated in the presence of humidity.



Packs & Colors

Available in the following packing:

NEUTRAL Version

Base kg. 12,070 + Reag. kg. 2,610 = total kg. 14,680 B+R;

COLORED Version (standard colors)

Base kg. 12,570 + Reag. Kg. 2,610 = total kg. 15,180 B+R;

COLORED Version (p10)

Base kg. 13,540 + Reag. Kg. 2,610 = total kg. 16,150 B+R.

Colors available in the Pava color chart. ΔE Cielab <5.0 non-binding.

Warnings

If at the opening of the container the products show signs of instability/deterioration including thickening, crystallization, gelatinization, sedimentation, flotation, etc. due to incorrect storage of the material (temperature/humidity) both during transport and in the final warehouse or for use beyond the expiration date, the use is not recommended.

Product for professional use.

It is strongly recommended to use the applicators course before using Pava Resine products. Anyone who uses these products without being enabled, does so at their own risk.

Keep out of reach of children. Ventilate the premises well during use and drying. Do not eat, drink or smoke during use. During use, wear protective gloves and goggles and use the usual precautions for handling chemical products. In case of contact with eyes or skin, wash immediately with plenty of water and consult a doctor. If swallowed contact a poison control center or a doctor immediately. Ventilate the premises before staying there.

Rules to be observed

The above mentioned products and technologies results low-environmental impact and permit to reduce the internal and external pollution caused by solvents. Compliance to the hygienic standards in force as the use of epoxy resins is strongly recommended. For more informations, see our Safety Sheet.

Handling Precautions

NOT RECOMMENDED FOR:

DO NOT apply on concrete which is less than 10 days old.

DO NOT apply on concrete with a curing or sealing membrane.

DO NOT apply on base concrete at a temperature lower than 10°C (50°F).

DO NOT dilute with ethyl alcohol.

SLIP/FALL PRECAUTIONS: We recommend using slip resistant granules in all outdoor applications where the product will be used and on indoor applications that may be exposed to water, oil or other spills that may cause a slippery environment. Polymer or glass microfibers may be added into the product to achieve the amount of slip resistance desired. It is the end user's responsibility to determine the suitability of a coating for their particular application. Pava Resine will not be responsible for injury incurred in a slip/fall accident.

SAFETY PRECAUTIONS: Health Considerations: Consult our Safety Data Sheet.

Chemical systems require the use of proper safety equipment and procedures. Please follow our Safety Data Sheet for detailed information and handling guidelines.

For Your Protection: the information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Pava Resine. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and methods herein suggested. The toxicity and risk characteristics of products made by Pava Resine will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, Pava Resine makes no warranty of any kind, express or implied, other than that the material conforms to its applicable current Standard Specifications. Pava Resine hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

QR CODE: IN CASE OF NO-DOWNLOAD FROM THE LABEL REQUIRE THE NEW ISSUE. The indications contained in the technical data sheet are the most up-to-date available at our disposal on which we reserve all appropriate changes; however such information must be considered without any binding value and will not demonstrate any contractual legal relationship or ancillary obligation with the purchase contract. Since the use of the product also takes place outside of our control, the responsibility for the incorrect use of the product falls exclusively on the user and therefore does not involve the assumption of our guarantee and responsibility for the final result of the work. Moreover, they do not exempt the customer from the burden and exclusive responsibility of verifying the suitability of our products for their use and the intended purpose; in addition, the customer is required to verify that the values shown in the technical data sheet are also valid for the batch of product of interest and are not obsolete and/or replaced by successive editions. This sheet cancels and replaces the previous ones.

